




Rev.	Date	Checked	Description
			
			
Specific Gravity: 1.15 // Shore A Hardness: 62° // Tensile Strength: 11.5MPa // Elongation at Break: 440% // Tear Strength: 22kN/m // Compression Set (22h/177°C/25%): 34% // Rebound Resilience: 55% High Transparency Silicone: Silicone for calendaring and extrusion. High transparency. Good compromise of overall properties.			
Tolerances: ISO-3302-1:1996 CLASS E-2		Dim.: 23,00 x 27,30m Color: Translucent - No RAL	
		Material/Aditives: TS60	
	Date	Name	MOQ: 75m
Designed		MEREFSA	Coils: 3 x 25m
Verified		MEREFSA	Hardness: 60 Shore A
Approved			Weight: 384,0gr/m
Quality			Filename: p16f.pdf
Quality			Customer Ref.:
			Title:
			Ref.: p16f
			
			Scale: 2:1
			A4