

PTFE - Politetrafluoretileno

Tabla de resistencia

RESISTENCIA DEL COMPUESTO

Chemical Products	PTFA
Acetaldehyde	Excellent
Acetone	Excellent
Aluminium Sulphate	Excellent
Ammonium Chlorate	Excellent
Ammonium Hidroxide	Excellent
Aniline	Excellent
Benzene	Excellent
Boric acid	Excellent
Brine	Excellent
Bromium (Anhydrous)	Excellent
Carbon disulphate	Excellent
Chloracetic acid	Excellent
Clorobenzene	Excellent
Chloroform	Excellent
Cromic acid	Excellent
Citric acid	Excellent
Diethyl ether	Excellent
Ethyleneglycol	Excellent
Fatty acids	Excellent
Iron chlorate	Excellent
Iron sulphate	Excellent
Fluorosilic acid	Excellent
Formic acid	Excellent
Freon (liquid)	Excellent
Hydroborid acid	Excellent
Hydrochloric acid	Excellent
Hydrocyanic acid	Excellent
Hydrofluoritic acid	Excellent
Acido solution of iron sulphate	Excellent
Maleic acid	Excellent
Mercury salts	Excellent
Naphta	Excellent
Naphtaline	Excellent
Nickel salts	Excellent
Nitric acid (0-50%)	Excellent
Nitrobenzene	Excellent
Phenol	Excellent
Phosphoric acid	Excellent

PTFE - Politetrafluoretileno

Tabla de resistencia

Chemical Products	PTFA
Phtalic acid	Excellent
Picric acid	Excellent
Pyridine	Excellent
Salicilic acid	Excellent
Silver nitrate	Excellent
Sodium carbonate	Excellent
Sodium hydroxide	Excellent
Sodium nitrate	Excellent
Sodium peroxide	Excellent
Sodium silicate	Excellent
Sodium sulphat	Excellent
Sulphuric acid	Excellent
Tannic acid	Excellent
Tartaric acid	Excellent
Trichloroethylene	Excellent
Zinc chlorate	Excellent