

Description

Temperature crosslinkable fluorosilicone elastomer.

Characteristics

- Good mechanical properties
- Good resistance to oils
- Wide range of working temperatures: -50°C to 200°C

PROPERTIES	FLUOR SILICONE
Type (AFNOR T 40002)	FMVQ
DENSITY [g/cm ³]	1.41
HARDNESS [SHORE A]	60
BREAKING STRENGTH [Mpa]	8.2
ELONGATION [%]	263
SECANT MODULUS AT 100% ELONGATION	3.1
TEAR RESISTANCE	18

Storage

Preserved in unopened original packaging, can be stored for 3 months at temperatures below 30°C from the date indicated on the packaging.

